

BEST AVAILABLE COPY

EXHIBIT 2

Microelectronic Grade Silicone Materials for CSP

Stanton Dent,

Mike Gaul, Ann Norris

Dow Corning Corporation



SEMI
EDUCATION


Outline

- The nature of silicones
- Silicone polymerization
- Root cause of silicone outgassing
- Development of materials for use in the μ BGA package
 - Resolution of Lead bond issues
 - X-ray Photoelectron Spectroscopy images
- Conclusions

Chemical Nature of Silicones

Degree of Alkyl Substitution

0




SiO_2

Silica

Glasses

Hard & Brittle

1




$\text{R}_1\text{SiO}_{3/2}$

Silicone resins

Silsesquioxanes

2





R_2SiO

Silicone

polymers

Soft & Flexible

Properties of Silicone Fluids



- Wide OSiO angle \Rightarrow Free rotation, low T_g , T_m , etc
- Strong Si-O Bond \Rightarrow High Thermostability
- PDMS backbones are covered by CH_3 's, hydrophobicity



Silicone Properties*

- Liquid at high molecular weight
 - Low apparent activation energy for viscous flow
 - Low surface energy
 - High gas permeability
 - High dielectric strength
 - Thermal stability
 - Oxidative resistance
 - Low boiling points
 - Excellent flammability properties
 - Low surface shear viscosity
- * Relative to hydrocarbon materials

Equilibration Polymerization of Silicones

- Acid or base catalysis
- Time, temperature and solvent effects
- Molecular weight control
 - End block
 - trimethylsilyl
 - dimethylhydroxyl
 - dimethylvinyl
 - others

Equilibration Polymerization of Silicones

- Polymerization:




- Equilibrium mixture of cyclics and linears
 - High Mw linear polymer
 - Typically 11-18 wt. % cyclics for PDMS
- Low molecular weight species are very volatile and low viscosity




Low Mw Silicones

Compound	Viscosity @ 25 C cS	Boiling Point C	Mw
Water	1.0	100	18
MM	0.7	101	162
D ₃		135	222
MDM	1.0	153	237
D ₄	2.3	175	297
MD ₂ M	1.5	196	311
D ₅	3.9	211	371
MD ₃ M	2.1	230	385
D ₆	6.6	245	445
MD ₄ M	2.6	260	459
D ₇	9.5	276	519
MD ₅ M	3.2	287	533
D ₈	13.2	303	593
MD ₆ M	3.9	310	607
D ₉	18.0	326	667
MD ₇ M	4.5		681



M(D)_nM

Linear series



D₄

Cyclic series



Removal of Low Mw Species

- Vacuum strip dependent on:
 - time, temperature, vacuum level
- Liquid-liquid solvent extraction
- Non-solvent precipitation
- Super critical fluid extraction
- High pressure liquid chromatography





SEMI
EDUCATION



Gas Chromatography

Compounds	Non- microelectronic Grade	Microelectronic Grade
	PPM	PPM
D4-D12	20600	0
D13-D20	11860	734

- Greater than 95% reduction in low Mw species
- Remaining material is high Mw
 - high viscosity & high boiling






Typical Silicone Formulation


- Silicone polymer
 - outgassing
- Filler
- Crosslinker
- Adhesion promoter
- Catalyst (Pt)



Condensation Cure




Addition Cure



- No cure by-products
- Heat activated
- Can be 1-part or 2-part



μ BGA Package



SEMI
EDUCATION

Material and Process Considerations for CSP Lead Bonding

- Design considerations
 - Nubbins or pads
 - Proximity to lead bond area
- Material considerations
 - Rheology
 - Low volatility
 - Low creep
- Off set stencil printing
 - Gross contamination during printing
 - Time between print and cure



Non-microelectronic grade materials led to:

- Migration of silicone onto leads
 - Cure silicone nubbins
 - Self diffusion of low M_w components
 - $D \propto 1/M_w^2$
 - Surface spreading
 - $\eta \propto M_w$
 - Outgassing



Use of non-microelectronics grade silicones led to increases in:

- Lead bond ultrasonic frequency
- Cleaning frequency of lead bond tip
- Deformation of the lead
 - High failure rate due to heel breaks




Microelectronics grade silicone material eliminated all problems:


- Increased yield
- Increased productivity
- Increased reliability



XPS of TAB tape showing leads



Non-Microelectronic Grade Silicone



Microelectronic Grade Silicone



SEMI
EDUCATION

Summary

- Silicones have unique properties due to their chemical composition.
- Equilibration polymerization of silicones
 - Low Mw species present - root cause
 - Can be removed by further processing
- Not all silicone materials are alike
- Low outgassing microelectronic grade silicone material set is commercially available.
- Companies are in production with μ BGA using a low outgassing silicone material set.



**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☒ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☒ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☒ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.